

Ab

PRODUCTION OF NYLON 6

Patent number: JP62252426
Publication date: 1987-11-04
Inventor: OKADA AKANE; others: 03
Applicant: TOYOTA CENTRAL RES & DEV LAB INC
Classification:
- international: C08G69/16
- european:
Application number: JP19860095781 19860424
Priority number(s):

Abstract of JP62252426

PURPOSE: To facilitate the production of nylon 6 of a desired crystalline structure (alpha or gamma-form), by polymerizing a monomer for nylon 6 in the presence of a silicate at a temperature higher than the melting point of the monomer and cooling the product at a specified cooling rate.

CONSTITUTION: 100pts.wt. monomer (A) for nylon 6 (e.g., caprolactam) is polymerized in the presence of 0.001-100pts.wt. silicate (B) (e.g., montmorillonite), desirably, swollen with an organic substance (e.g., 12-aminododecanoic acid hydrochloride) at a temperature higher than the melting point of component A (about 220 deg.C), and the product is cooled at a cooling rate ≤ 4 deg.C/min from the melting point or above to 160 deg.C or below to obtain a composite of nylon 6 of an alpha crystalline structure with the silicate or cooled at a cooling rate ≥ 10 deg.C/min to obtain a composite of nylon of a gamma crystalline structure. This composite is dissolved in a solvent (e.g., m-cresol), and the silicate is removed to obtain nylon of an alpha or gamma crystalline structure.

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan